




綺利人造石

透光雲石(雪花石) 透光木紋石 透光鳳凰石 透光玉石
透光類真石 透光真石板 檯面人造石



試驗報告

報告編號：HB-11-02065X

C-11-06186

頁 數: 1 OF 1

報告日期：100 年 04 月

報告日期: 100 年 09 月 15 日

主	： 綺利國際有限公司
位	： 綺利國際有限公司
稱	： 透光人塗窗石
員	： 綺利國際有限公司(李臣)
期	： 100年 04月 01日
日	： 100年 04月 11日 - 100年 04月 13日
註	： 以上資料由顧客提供(收件及試驗日期除外)

試驗結果：

試驗項目	試驗方法	試驗結果
耐酸性	參考 CNS 2215(2006)	表面無異狀
耐鹼性		表面無異狀
含水率(%)	參考 CNS 3802(2008)	0.3

註：本試驗之樣品不在 TAF 認可範圍內，故無法出具 TAF 標誌之報告。

規範要求僅供參考，合格之判定以委託單位實際評定為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sampled lot(s). This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有注明，此测试报告的数据仅指所抽样的样品。本测试报告未经许可，不得擅自复制或转载。

This document is issued by the Company subject to its General Conditions of Service provided herein, available on request or accessible at www.spa.com/terms_and_conditions.htm, for electronic terms documents, subject to "Terms and Conditions for Electronic Documents at www.spa.com/terms_and_conditions.htm. Attention is drawn to the limitations of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the current status of the Company's affairs and is not intended to constitute an offer, recommendation or solicitation of securities. The Company and its officers, directors, employees, agents, and advisors make no representation or warranty as to the accuracy or completeness of the information contained herein, and the Company and its officers, directors, employees, agents, and advisors make no representation or warranty as to the accuracy or completeness of the information contained herein, and the Company and its officers, directors, employees, agents, and advisors make no representation or warranty as to the accuracy or completeness of the information contained herein. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

STS Taiwan Ltd. No. 31, 32, 33, 34, 35, Wu Diye Road, Wuku Industrial Zone, Tainan County, Taiwan / 台北縣五股工業區五股路31號, 32號, 33號, 34號, 35號
台灣檢驗科技股份有限公司 1 (886) 21 2289-2155 f (886) 21 2289-2152 www.cn.sps.com

Member of SESQ Division



經濟部標準檢驗局 試驗報告

報告號碼：9A300000355

申請者：緯利國際有限公司

品名：人造透光雲石

格：(空白)

規格：(空白)
型號：(空白)

受理日期：100 年 03 月 07 日

完成日期：100 年 05 月 04 日

試 驗 項 目	試 驗 結 果
防焰性 炭化長度 餘焰 餘煙 煙頭 燃燒性 20mm 垂直燃燒試驗	0 cm 0 秒 於 1 分鐘後無餘燭 10 秒加熱時間，防焰為 1 級 符合 V-0 之規定

試驗說明

1. 測試期間：100 年 3 月 7 日 至 100 年 5 月 4 日

2. 試驗方法：

2.1(1)試驗項目：防焰性參照 CNS 7614 進行試驗

(2)試驗項目：燃燒性參照 CNS 14535 進行試驗

2.2 儀器設備：防搶性項目（財產編號：110-3100906-0028-0000005-003）

燃燐性項目(財產編號：3101103-520-010、3-5243)

2.3 試驗地點：10051 臺北市中正區濟南路 1 段 4 號

3. 報告內容如有疑問，請洽本局：第六組高分子檢驗科

聯絡電話：02-23431876 傳真：02-23431883

其它事項或備註：


1. 防銹性一項，試樣經 CNS 7614 A 法處理

樣品資料：

(以下空白)

第 2 頁 / 共 3 頁


副本




ST-5002



ST-5003




ST-5004




ST-5005



ST-5006




ST-5007




ST-5009

檯面人造石

提供連工帶料安裝施工服務・詳細請洽本公司服務人員・



ML-101




ML-108



ML-112



ML-116




ML-118



ML-124



ML-125



ML-126




ML-127



ML-130




ML-201




ML-202



ML-203




ML-229




ML-232



ML-233




ML-237




ML-316





本系列產品係由真石膠合而成，裁切時請建議送至專業石材廠切割。


透光真石板



MK-7006



MK-7018



MK-8021



MK-8022